



TOKEM MB-65 (P)

TR 20.16.59-039-72283630-2016

TOKEM MB-65 (P) is a ready equimolar mixture for nonregenerable mix bed filters. It consists of high purity strong base anion exchange resin and strong acid cation exchange resin (1 : 1 in capacity).

GENERAL DESCRIPTION

Matrix	styrene-DVB
Functional group	Sulfonic acid/quaternary amine (type 1)
Polymer structure	gel
Ionic form	H ⁺ / OH ⁻ Hydrogen / hydroxyl

Application area:

- for mix bed filters and cartridges to produce ultrapure water with electric conductivity of up to 0.056 μ S/sm; it is applied in manufacturing electronics, in medicine and other fields of industry and science;
- for purification of potable water.

Physical and Chemical Characteristics:

CHARACTERISTICS	STANDARD VALUE	
Appearance	Spherical grains, light yellow to brown in colour	
Components	Cation exchange resin	Anion exchange resin
Component content in the mixture, volume %	35 \pm 5	65 \pm 5
Total capacity, mmol/cm ³ (mg-eq/cm ³), min	1.9	1.15
Mass fraction of chloride ions, mg/cm ³ , max	0.01	0.40
Water product oxidation in oxygen equivalent, max	0.5 mg/g	0.5 mg/dm ³
Moisture retention, %	50-60	
Difference between settling times of anion and cation resins, sec, max	6	
Electrostatic coefficient, % max	20	
PARTICLE SIZE DISTRIBUTION		
Mean particle size, mm	0.40-1.25	
Volume of effective size fraction, % min	98	
Total uncracked beads as shipped, %, min	97	